

In the Claims:

Please amend claims 5 and 15 as set forth in the attached "Listing of Claims".

LISTING OF CLAIMS

Claim 1 (Canceled)

Claim 2 (Previously Presented): Compositions according to Claim 15, wherein the polyester is selected from PET and PBT.

Claim 3 (Previously Presented): Compositions according to Claim 15, comprising up to 30 parts by weight of copolyetherester per 100 parts of thermoplastic polyester.

Claim 4 (Withdrawn): Compositions according to Claim 15, comprising up to 30 parts by weight of polycarbonate per 100 parts of thermoplastic polyester.

Claim 5 (Currently Amended): Compositions according to Claim 15, wherein the copolymer (A) comprises an elastomer core and at least one thermoplastic shell.

Claim 6 (Canceled)

Claim 7 (Previously Presented): Compositions according to Claim 15, wherein the ethylene-unsaturated epoxide copolymers (B2) are ethylene-alkyl (meth)acrylate-unsaturated epoxide copolymers obtained by copolymerization of the monomers and contain from 0 to 40% by weight of alkyl (meth)acrylate and up to 10% by weight of unsaturated epoxide.

Claim 8 (Previously Presented): Compositions according to Claim 15, comprising, per 100 parts by weight, 75 to 95 parts of polyester for 25 to 5 parts of impact modifier, respectively.

Claims 9-14 (Canceled)

Claim 15 (Currently Amended): Thermoplastic polyester compositions comprising, by weight:

(i) from 60 to 98% by weight of a thermoplastic component consisting of a thermoplastic polyester; and

(ii) from 2 to 40% by weight of an impact modifier consisting of:

(a) a core-shell copolymer (A) having a single shell; wherein the core consists of one or more polymers selected from the group consisting of isoprene homopolymers, copolymers of isoprene with at most 30 mol% of a vinyl monomer selected from the group consisting of styrene, alkylstyrene and alkyl (meth)acrylate, copolymers of butadiene with at most 30 mol% of an alkyl (meth)acrylate, and copolymers of alkyl (meth)acrylate with more than 0 mol% and at most 30 mol% of a vinyl monomer selected from the group consisting of styrene and alkylstyrene; further wherein the shell consists of one or more polymers selected from the group consisting of styrene homopolymers, alkylstyrene homopolymers, methyl methacrylate homopolymers, and copolymers consisting of at least 70 mol% of a styrene, alkyl styrene or methyl methacrylate with at most 30 mol% of a vinyl acetate; and

(b) an ethylene copolymer (B) chosen from ethylene-unsaturated epoxide copolymers (B2);

(iii) the (B2)/(A) ratio being between 40/60 and 10/90 for proportions of impact modifier between 18 and 40% in 82 to 60% of polyester, respectively;

(iv) the (B2)/(A) ratio being between 40/60 and 25/75 for proportions of impact modifier between 2 and 18% in 98 to 82% of polyester, respectively.